



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>B29C 59/02, B42D 15/10, G03H 1/02,</b> <b>B65D 33/00, B44F 1/02</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/35662</b> <b>(43) International Publication Date:</b> <b>22 June 2000 (22.06.00)</b>
<b>(21) International Application Number:</b> <b>PCT/US99/28997</b> <b>(22) International Filing Date:</b> <b>7 December 1999 (07.12.99)</b> <b>(30) Priority Data:</b> <b>98870270.0 14 December 1998 (14.12.98) EP</b> <b>(71) Applicant (for all designated States except US):</b> THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> VAN GEERT, Peter, Maurits, Maria [BE/BE]; Potaardestraat 75, B-1950 Kraainem (BE). ETESSE, Patrick, Jean-François [FR/BE]; Boulevard Louis Schmidt 63, B-1040 Brussels (BE). <b>(74) Agents:</b> REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217-1087 (US).		<b>(81) Designated States:</b> AE, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), DM, EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SI, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> DUPLEX HOLOGRAPHIC FILM <b>(57) Abstract</b> <p>The present invention relates to an holographic structure comprising an organic solvent based embossed layer, a metallic layer located onto the embossed layer, and an organic solvent based printing ink layer characterised in that the printing ink layer and the metallic layer are solely separated by a water solvent based primer.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## DUPLEX HOLOGRAPHIC FILM

5

### Technical field

The invention relates to a film structure for a holographic film.

10

### Background of the invention.

Holographic films are used more and more widely, particularly in the packaging of consumer goods. In an holographic structure, an embossed layer is covered with a metallic layer. This has the advantage of providing a three dimensional structure effect which is catching to the eye. However, this often requires redesign of the whole film structure, particularly due to the fact that the metallic layer is not a thermo-plastic layer but a thin metallic layer.

15

20

The present invention concerns an holographic structure comprising an organic solvent based embossed layer, a metallic layer located onto the embossed layer, and an organic solvent based printing ink layer.

25

Among the advantages of such a structure is the eye-catching effect which can be obtained by the combination of holographic techniques and the holographic techniques.

30

While having this and other advantages, such structures, particularly when integrated into laminated film structures, have

disadvantages. For example, a typical film structure will comprise the organic solvent based lacquer printed or applied, prior to embossement, onto a first side of a polyester (PET) film, typically a 12µm thick film. Once this lacquer is applied to this PET film, it is embossed so as to produce the holographic pattern. Once embossed, a metallic layer, typically aluminium, is vaporised or applied in another manner onto the embossed lacquer to form the "holographic core". The PET side which is not covered by the embossed lacquer can be thereafter laminated to other films, for example a 180 µm thick PE poly-ethylene film. Once this is done, printing can occur. However, it was found that direct printing onto the metallic layer was leading to dissolution of the embossed layer by penetration of the ink solvents through the thin metallic layer.

However, all these film structure are showing dissolution of the embossed lacquer due to ink solvent going through the metallic layer.

The invention seeks to provide an holographic structure of the above mentioned kind which does not lead to dissolution of the embossed lacquer.

#### Summary of the invention

In accordance with the invention, this object is accomplished in a holographic structure of the above mentioned kind in that the printing ink layer and the metallic layer are solely separated by a water solvent based primer.

A process in accordance with the invention has a number of advantages. Since the metallic layer and the printing ink layer are

separated by the water solvent based primer, migration of the organic solvent from the ink layer to through the water solvent based primer is prevented, as the organic solvent was found not to migrate through a water solvent layer. Therefore, dissolution of the embossed lacquer by migration of the organic solvent present in the ink layer is avoided.

#### Detailed description of the invention

The invention relates to an holographic structure. By an holographic structure, it should be understood that the structure is exhibiting a three dimensional eye-catching impression based on the metallisation of an embossed layer. Indeed, according to the holographic structure comprises an organic solvent based embossed layer. By organic solvent based, it should be understood that the layer is applied together with a solvent, for example by a printing technique, the solvent being organic. The layer is embossed by processes already known by the man skilled in the art of making holograms. Typically, embossement is obtained by application of a pressure onto the layer, so as to produce the pattern which will exhibit the holographic effect. This holographic effect is produced in combination with the metallic layer located onto the embossed layer. Typically, this metallic layer is an aluminium layer, which is applied by vaporisation, thereby giving a thickness of a few atomic layers. Further, the holographic structure comprises an organic solvent based printing ink layer. This layer may comprise one or more inks having various colours, these being typically applied by the usual printing techniques together with a solvent, which is an organic solvent in the structure of the invention. It should be mentioned that an organic solvent should be understood as being non aqueous. Additionally, the printing ink layer and the metallic layer

are solely separated by a water solvent based primer. By solely separated, it should be understood that no laminated layers are to be found between the printing ink layer and the metallic layer. It is necessary that the primer is water-based so as to prevent migration of the solvent from the inks into the embossed layer through pin-holes which usually are present in the thin metallic layer. Indeed, migration of organic solvents through the metallic layer was found to dissolve the embossed layer. It should be understood that the primer could comprise several layers itself, although such layers should not be laminated but applied together with a water based solvent.

In a preferred embodiment, the embossed layer is formed from a lacquer applied to a thermoplastic film, the thermoplastic film being preferably a poly-ethylene-terephthalate film. In a more preferred embodiment, this thermoplastic film is laminated to another thermoplastic film, such as a polyethylene film for example.

In the most preferred embodiment according to the invention, the embossed layer is an acrylic based lacquer which is deposited on a 12  $\mu\text{m}$  polyester film using toluene, butyl acetate or ketones as an organic solvent. This embossed layer is thereafter covered with an aluminium layer, which is itself covered with the water solvent based primer which is an aqueous based acrylic, as in a preferred embodiment whereby the water solvent based primer comprises acrylic compounds. The primer is therefore forming a barrier to the migration of the organic solvents comprised in the printed ink layer which is applied onto the primer. In this most preferred embodiment, a white ink and colored inks are printed, the white ink having an ethyl-acetate solvent and the coloured inks having an ethanol solvent. Indeed it was found preferable to

use different organic solvents for the ink in order to avoid dissolution of a first ink when a second ink is applied. Indeed, in a preferred embodiment, the printing ink layer comprises a coloured ink and a white ink, the coloured ink having ethanol as an organic solvent and the white ink having ethyl-acetate as an organic solvent. A two-components lacquer is then applied onto the printed ink layer to protect the ink. The side of the PET film which is not covered by the embossed layer is then laminated to a 180  $\mu\text{m}$  polyethylene film. A package made from this film laminate comprising an holographic structure according to the invention allows to avoid dissolution of the embossed layer while maintaining the holographic appearance. Further, this package revealed to be suitable for use as a refill pouch for laundry product when made according to the process described in EP626319. Further, this package can be used to contain up to 3 liters of liquid laundry product, filling occurring at normal production speed, without need for an enlarged head space as would be needed in case of a thicker and more rigid film. Another package is foreseen, whereby each side of the film is made from a thermoplastic material. This may be achieved by applying an extra thin layer of polyethylene, such that both sides of the film could be thermo-sealed. Such a package is particularly well suited for granules laundry products packaging.

## WHAT IS CLAIMED IS:

1. An holographic structure comprising an organic solvent based embossed layer, a metallic layer located onto the embossed layer, and an organic solvent based printing ink layer characterised in that the printing ink layer and the metallic layer are solely separated by a water solvent based primer.
2. A structure as in claim 1, whereby the embossed layer is formed from a lacquer applied to a thermoplastic film.
3. A structure as in claim 2, whereby the thermoplastic film is a polyester film.
4. A structure as in claim 2, whereby the thermoplastic film is laminated to another thermoplastic film.
5. A structure as in claim 1, whereby the metallic layer is an aluminium layer.
6. A structure as in claim 1, whereby the embossed layer is an acrylic based lacquer.
7. A structure as in claim 1, whereby the printing ink layer comprises a coloured ink and a white ink, the coloured ink having ethanol as an organic solvent and the white ink having ethyl-acetate as an organic solvent.
8. A structure as in claim 1, whereby the water solvent based primer comprises acrylic compounds.



9. A package made from a film laminate comprising an holographic structure as in claim 1.

5 10. A package as in claim 9, whereby each side of the film is made from a thermoplastic material.

## INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 99/28997

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B29C59/02 B42D15/10 G03H1/02 B65D33/00 B44F1/02

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B29C B42D G03H B65D B44F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 319 475 A (KAY RALPH ET AL) 7 June 1994 (1994-06-07) column 2, line 66 -column 3, line 8 column 4, line 6 - line 63 column 5, line 37 -column 6, line 8 column 7, line 50 -column 8, line 49 column 11, line 17 -column 12, line 19	1-6,8-10
X	WO 93 16888 A (DE LA RUE HOLOGRAPHICS LTD) 2 September 1993 (1993-09-02) page 3, line 21 - line 33 page 7, line 13 -page 8, line 1 page 14, line 1 -page 15, line 4	1-6,8
	-/-	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

24 March 2000

Date of mailing of the international search report

31/03/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3018

Authorized officer

Lindner, T

# INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 99/28997

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>WO 97 34170 A (CHOCK ERNEST)  18 September 1997 (1997-09-18)  page 1, line 23 - line 29  page 3, line 24 - line 31  page 6, line 9 - line 29</p>	1-6
X	<p>US 5 267 753 A (CHOCK ERNEST)  7 December 1993 (1993-12-07)  column 2, line 65 -column 3, line 38</p>	1
A	<p>US 4 999 075 A (COBURN JR JOSEPH W)  12 March 1991 (1991-03-12)  column 2, line 14 - line 29  column 4, line 58 -column 5, line 19</p>	1-8

# INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 99/28997

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5319475 A	07-06-1994	AT 144338 T	15-11-1996
		DE 69122755 D	21-11-1996
		DE 69122755 T	06-03-1997
		DK 530267 T	24-03-1997
		EP 0530267 A	10-03-1993
		ES 2096649 T	16-03-1997
		WO 9118377 A	28-11-1991
		GB 2260514 A,B	21-04-1993
		GR 3021854 T	31-03-1997
WO 9316888 A	02-09-1993	CA 2128789 A	02-09-1993
		DE 69315985 D	05-02-1998
		DE 69315985 T	16-04-1998
		EP 0626909 A	07-12-1994
		GB 2278577 A,B	07-12-1994
		JP 7503674 T	20-04-1995
WO 9734170 A	18-09-1997	AU 2174897 A	01-10-1997
		CN 1193299 A	16-09-1998
US 5267753 A	07-12-1993	AU 3932793 A	21-10-1993
		WO 9318924 A	30-09-1993
US 4999075 A	12-03-1991	JP 3027983 A	06-02-1991